

lucitelux™ with microban®

TECHNICAL BULLETIN

On an unprotected product, bacteria can double in number every 20 minutes! Microban® antimicrobial technology works 24/7 to keep Lucite® continuous cast acrylic sheet cleaner between cleanings by inhibiting the growth of bacteria that can cause stains, odors and product deterioration. Upon contact, Microban technology begins to work immediately disrupting the ability of the microorganism to function, grow and reproduce.

Only Lucite® continuous cast acrylic sheet has built-in Microban antimicrobial technology for an added level of cleanliness protection you can count on for the lifetime of your product.

FEATURES & BENEFITS

- Pink Masking.
- Withstands heavy-duty, continuous use.
- More impact resistant than glass.
- Allows for easy fabrication and fitting.
- Broad scope for thermoforming into complex curved shapes.
- Smooth, glossy surface that is comfortable and warm to the touch.
- Easy to clean.

APPLICATIONS

- Medical Applications
- Bassinets
- Glove Box Dispensers
- Paper Towel Dispensers
- Test Tub Holders
- Facial Tissue Dispensers
- Supply Organizers
- Food Applications
- Sneeze guards

FABRICATION

Machining

Microban® can be cut, drilled and shaped using traditional acrylic fabricating techniques.

To avoid scratching during such procedures, masking should remain in place as long as possible.

Cementing

Microban® can be cemented using solvent cement, embodied cement and two-component polymerizable cements.

Painting

Microban® can be decorated using standard acrylic-based paints and silk-screen inks. As with any acrylic painting or screening operation, avoid heavy coats of paint or excessive flooding of screen inks which allow solvents or thinners to remain in contact with the acrylic surface and cause crazing.

Recommended Paints:

- Grip-Flex®, Wyandotte Sign Finishes, Norcross, GA.
- Lacryl®, Spraylat Corporation, Mount Vernon, NY.
- Recommended Screen Inks:
- Multi-Vac Series® Inks, Advance Excello, Chicago, IL.
- 70,000® Series Inks, Naz-Dar Company, Chicago, IL.

• *Continued on next page.* •

*For sales and information,
please contact Jane Nash
1-800-4-LUCITE x 2426*

(JUL. 1, 2011)

lucitelux™ with microban®

TECHNICAL BULLETIN

THERMOFORMING

Microban® can be thermoformed to any contour – from subtle curves to complex shapes. The forming temperature range recommended for shaping sunbed covers is 320°F +/- 10°F.

Heating Methods

There are two basic heating methods utilized in forming Microban®:

- Vertical oven heating
- Horizontal oven heating

If a vertical oven is used, it may be necessary to trim off the edges where clamp marks are present. Clamp along the short edge, exercising great care to ensure the sheets are not exposed to temperatures above 320°F; otherwise stretching of the sheet may occur.

To prevent surface marring, sheets should be loaded onto supporting trays covered with layers of felt or similar material. Dimensional changes will occur when an acrylic sheet is heated freely in an air oven and drape molded without clamping.

The inherent strain present in continuous cast acrylic sheet is relaxed when heated, giving rise to some shrinkage. Precise shrinkage is dependent upon variables such as cycle time, heating temperature, and forming method.

CLEANING

Microban® provides excellent resistance to staining from dirt, bacteria or perspiration. It also resists chemical attack from crazing agents such as household cleaners, cosmetics and mild disinfection agents.

To clean acrylic sheet:

- Dissolve mild liquid detergent in cool water.
- Dip soft, clean cloth in solution and wring out.
- Wipe the surface of the sheet.
- Allow surface to dry naturally, or wipe with a separate cloth slightly dampened with solution.

WARNING: Do not allow concentrated disinfectant, surgical or methylated spirits, any liquid containing alcohol or any other solvents to come in contact with LUCITE® MICROBAN® ACRYLIC SHEET.

DISINFECTION

To disinfect acrylic sheet:

- Dilute an antiseptic or hospital concentrate with cool or cold water in the amount recommended on the label for general disinfection.
- Wipe the surface as described under CLEANING.

CAUTION: When using acrylic sheet in conjunction with applications where electrical units are attached, the unit must be unplugged before cleaning or disinfection. Great care must be taken to see that no water or solution enters the electrical compartment.

DUSTING

Use a soft, clean, slightly damp cloth when dusting. Never use a dry cloth. This tends to generate a static charge which will attract more dust.

POLISHING

If the surface of Microban® acrylic sheet becomes scratched, it can generally be restored by using a polishing paste designed for use with acrylic or a mild abrasive metal polish applied on a soft clean cloth. If the scratches are too deep to be removed by this method, use a piece of 600 grade waterproof sandpaper (wet). When the surface is smooth, the gloss can be restored with metal polish. Power buffing is only recommended for professional fabricators.

*For sales and information,
please contact Jane Nash
1-800-4-LUCITE x 2426*

(JUL. 1, 2011)

TECHNICAL BULLETIN

PHYSICAL PROPERTIES

		Test Method	Typical Value ^(a)	
General	Specific Gravity	ASTM D792	1.19	
Mechanical	Tensile Strength ❖ % Elongation @ break ❖ Modulus of elasticity ❖ % Elongation @ yield	ASTM D638	11,000 psi 7.6% 465,000 psi 6.0%	
	Flexural Strength Flexural modulus (tangent)	ASTM D790	14,700 psi 461,000 psi	
	Impact Strength ❖ Compressive strength (x-y plane) ❖ Compressive stress @ yield ❖ Compressive modulus ❖ Charpy (un-notched) ❖ Charpy (notched) ❖ Shear Strength (punch tool) ❖ Izod (procedure A)	ASTM D695 ASTM D256 ASTM D6110 ASTM D732 ASTM D256	83,300 psi 18,000 psi 279,000 psi 5.0 ft lb/in/in 20.8 J/m 11,200 psi 0.32 ft-lb. / in.	
	Rockwell Hardness	ASTM D785	M-92	
	Residual Shrinkage (b) (Internal Strength)	ASTM D702	2.5 % maximum	
	Optical	Refractive Index	ASTM D542	1.49
		Light Transmission, Total	ASTM D1003	92%
	Haze	ASTM D1003	Less than 1%	
	Surface Abrasion Resistance (c) (Taber , CS-10)	ASTM D1044	500 cycles : < 1% 1000 cycles: <2%	
Thermal	Maximum Continuous Service Temperature		175°F (d)	
	Coefficient of Thermal Conductivity		1.45 Btu in./ft ² hr. °F	
	Deflection Temperature under load, 264 psi	ASTM D648	200°F	
	Hot Forming Temperature		280°-340°F (138°-170°C)	
	Coefficient of Linear Thermal Expansion	ASTM D696	3.5 E-05 in/in/°F	
	Specific Heat		0.35 Btu/ lb (°F)	
				• Continued on next page. •

Electrical	D-C Resistance ❖ Volume Resistivity ❖ Surface Resistivity	ASTM D257	>3.912E+15 Ω /cm > 5.237E+15 Ω /sq
	Dielectric Strength (2000v/sec)	ASTM D149	354 V/mil
	Dielectric Constant, k' ❖ 60 Hz ❖ 1 KHz ❖ 1MHz Dissipation Factor, D ❖ 60Hz ❖ 1KHz ❖ 1MHz	ASTM D150	3.3 3.0 2.7 0.06 0.04 0.02
	Arc Resistance	ASTM D495	No tracking
Combustibility	Smoke Density Rating Tunnel Test (smoke developed) ❖ 0.118" ❖ 0.236"	ASTM D2843	13.5%
	Rate of Flame Spread ❖ 0.118" ❖ 0.236"	ASTM E84	385 530
	Fuel contribution factor Ignition temperature	- ASTM D1929	11,300 Btu/lb 750°F (399°C)
	Radiant Panel, Flame spread index ❖ 0.118" ❖ 0.236"	ASTM E162	219 249
	Horizontal Burn ❖ 0.118" ❖ 0.236"	ASTM D635	1.18 in./min. 0.65 in./min
	UL Horizontal Burn Rating	UL94	94 HB (f1); (f2)
Miscellaneous			
Water Absorption	24 hrs @ 23°C 2 hrs boiling water immersion	ASTM D570	0.2% 0.6%
	Soluble Matter Lost (post immersion)	ASTM D570	nil
	Odour	-	nil
	Taste	-	n/a

Notes:

- Values provided should not be used for specification purposes. Some values will vary with sheet thickness.
- Measured at room temperature before and after heating above 300° F.
- Numerical values indicate % light transmission loss after indicated cycles.
- It is recommended that temperatures not exceed 180°F for continuous service

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should perform their own tests to determine the suitability of these products for their own particular purposes. Statements made herein should, therefore, not be construed as representations or warranties. The responsibilities of Lucite International, Inc. for claims arising out of breach of warranty, negligence, strict liability, or otherwise is limited to the purchase price of the material. Statements made herein concerning the use of the products or formulations described herein are not to be construed as granting a license to operate under any patent of Lucite International, Inc. or another, or as recommending the infringement of any patent of Lucite International, Inc. or another, and no liability for infringement arising out of any such use is assumed.

Microban® is a registered trademark of Microban Products Company.

*For sales and information,
please contact Jane Nash
1-800-4-LUCITE x 2426*

(JUL. 1, 2011)